



Munich Personal RePEc Archive

## **Product policies. characterization results ash by burning layer fluid**

Neamtu, Ion and Achim, Marian Lucian

"Titu Maiorescu" University of Bucharest, Romania

2009

Online at <https://mpra.ub.uni-muenchen.de/27200/>  
MPRA Paper No. 27200, posted 03 Dec 2010 20:46 UTC

## PRODUCT POLICIES. CHARACTERIZATION RESULTS ASH BY BURNING LAYER FLUID

*Lecturer, Ph.d. Ion NEAMȚU, "Titu Maiorescu" University of Bucarest*

*Lecturer, Ph.d. Marian-Lucian ACHIM, "Titu Maiorescu" University of Bucarest*

*Abstract: By economical and at the same time ecological reasons, industrial refuses (ashes) are being transported in waste dumps like offal's .To reduce the storage surfaces these offal's are incinerated and results a new refuse - the ash.(Ex. paper factories, thermo power stations).It's very important to find solutions to turn to good account the ash.*

### 1. THE MARK OF THE ASH RESULTED BY INCINERATING IN FLUID STRATUM

Studies were made using the two ashes resulted by incinerating *offal's*, in fluid stratum at a temperature of 700 - 800 Celsius degrees. Right after the ashes going out from the furnace these are mottled with water, to avoid the powdery, and after that are being transported to the waste dump.

The marks of these two ashes are presented in figures 1 and 2.

CHEMICAL COMPOSITION [%]	ASH A	ASH B
SiO <sub>2</sub>	37,2	31,6
Al <sub>2</sub> O <sub>3</sub>	21,2	16,0
Fe <sub>2</sub> O <sub>3</sub>	1,2	0,82
CaO	28,6	33,5
MgO	3,5	3,9
Mn <sub>2</sub> O <sub>3</sub>	0,06	0,03
P <sub>2</sub> O <sub>5</sub>	0,33	0,24
TiO <sub>2</sub>	0,55	0,44
BaO	-	0,02
SO <sub>3</sub>	0,58	0,22
K <sub>2</sub> O	0,67	0,50
Na <sub>2</sub> O	0,47	0,30
Cl	0,053	0,06
F	0,12	-
Loss at calcination	5,2	13,37
Total	99,7	100
CaO liber	1,6	-
S/(A+F)	1,65	1,88
A/F	18	19,51

Table 1.The chemical composition of A and B ashes used in experimental determinations.

ASH A		ASH B
Particles composition	Passing [%]	Phase composition (determined through DRX)
Riddle with och.: 1mm	100	Predominant phases:
500µm	100	- anorthic
250 µm	99,9	- gehlenit
125 µm	98	- amorphous phase

90 μm	91	Minor Phase:
63 μm	80	-calcite
45 μm	61	-dolomite
Sedimentare 40 μm	56	- quartz
30 μm	52	
20 μm	42	
15 μm	33	
10 μm	24	
5 μm	13	
2 μm	4	

Table 2. Particles size from ash A and phase composition of ash B used in experimental determinations.

In figure 1 it is presented the granulometrical composition of ash A determined with a granulometer with laser "analissette 22".




Figure 1. The granulometer curve of Ash A

To locate the two ashes in the ternary diagram CaO - Al<sub>2</sub>O<sub>3</sub> - SiO<sub>2</sub> were taken into account only those three oxides which have the weight in the ashes composition and it was recalculated the size of those three oxides (%) in table 3.

	SiO <sub>2</sub> [%]	Al <sub>2</sub> O <sub>3</sub> [%]	CaO[%]	Sum
Ash A	42,76	24,37	32,87	100,00
Ash B	38,96	19,73	41,31	100,00

Table 3. The oxide composition of those two ashes recalculated in the system CaO - Al<sub>2</sub>O<sub>3</sub> - SiO<sub>2</sub>




Figure 2. Locating the two studied ashes in the system CaO - Al<sub>2</sub>O<sub>3</sub> - SiO<sub>2</sub>.

It can be noticed that in the ternary system CaO - Al<sub>2</sub>O<sub>3</sub> - SiO<sub>2</sub> these ashes belong to the sub-system CAS<sub>2</sub> - C<sub>2</sub>AS - CS; Ash A belongs to the primary crystallization field of anorthic (C<sub>2</sub>AS), while ash B belongs to the primary crystallization field of gehlenit. The positions of these two ashes in the ternary diagram CaO - Al<sub>2</sub>O<sub>3</sub> - SiO<sub>2</sub> reflects compositional variation quite important of these two ashes, depending on the origin of the slam they come from.

Ash A behavior during the thermal treatment was observed through a graphic derivation analysis. It was used a graphic derivation machine called Paulik-Erdey MOM type, Budapest. The graphic derivation report obtained is presented in the figure 3

Starting from ashes' positions in the ternary diagram CaO - Al<sub>2</sub>O<sub>3</sub> - SiO<sub>2</sub> as well as taking into account the global oxide composition of all these, and also seeing all the information's from special literature regarding the usage concern of these ashes, can be synthesized the following potential way of turning them into good account:

- a) The main component in the raw material mixing to obtain portland.
- b) An addition to grind the portland (composites) clinker of cement.
- c) Raw material to produce the calcareous stone - silicon products.
- d) Raw material to produce crockery slates.
- e) Raw material to produce colored glazes for the vitreous type products.
- f) Raw material to frame some frittes for plaster rough cast emails.
- g) The granulation of ashes and their usage as aggregates to obtain some macro-porous products.
- h) Obtaining autoclave cellular concretes.




Figure 3. The graphic derivation report of the Ash A: the TG, DTG and ATD curves.

#### REFERENCE

- [1] E.M. Levin, Carl R. Robbins, Howard F. McMurdie - Phase Diagrams for Ceramists, The American Ceramic Society, Ohio 1994